

Z-scan technique for nonlinear optical characterization of bimetallic Au/Pd nanoparticles

R. Gutiérrez, J. Jiménez, J. Sánchez y Z. Correa

R. Gutiérrez, J. Jiménez, J. Sánchez y Z. Correa
Unidad Profesional Interdisciplinaria en Ingeniería y Tecnologías Avanzadas del IPN, Avenida Instituto Politécnico Nacional No. 2580, Colonia Barrio la Laguna de Ticomán Delegación Gustavo A. Madero, C.P. 07340 México, D.F., México.
jimenezp@fis.cinvestav.mx

M. Ramos., V.Aguilera., (eds.) .Ciencias Naturales y Exactas, Handbook -©ECORFAN- Valle de Santiago, Guanajuato, 2013.

Abstract

In this paper we present the nonlinear optical characterization of Au/Pd nanoparticles in order to obtain the nonlinear refractive indices using the Z-scan technique. The experiments were performed using a 514 nm laser beam Ar +, with 14Hz of modulation frequency, as excitation source. By using a lens the excitation beam was focused to a small spot and the sample was moved across the focal region along the z -axis by a motorized translation stage. Seven samples with different concentration ratio of Au/Pd nanoparticles were prepared by simultaneous reduction of gold and palladium ions in presence of poly (*N*-vinyl-2-pyrrolidone) (PVP) using ethanol as a reducing agent. In this work, we report the application of the Z-scan technique, to generate optical transmission of laser light as a function of the z position for solutions containing bimetallic nanoparticles of Au (core) / Pd (shell) with average sizes ranging from 3 to 5 nm. The magnitude of the obtained nonlinear refractive index was in the order of 10^{-7} to 10^{-8} cm²/W. Our results show that the nonlinear refractive index has a nonlinear behavior when the (Au/Pd) ratio was increased.

24 Backgrounds

Bimetallic nanoparticles (NPs) have attracted great interest among the scientific and technological community since they lead to many interesting size dependent electrical, chemical, and optical properties [1-3]. Specifically they often exhibit enhanced catalytic properties which differ from that of their monometallic counterparts, in thin films [4]. On the other hand, the studies for new nonlinear optical materials have increasing interest in the past years, due to the numerous applications in various fields such as optical communication devices and electronics [5]. Nanoparticles colloids in solution have been studied extensively because of their large third-order nonlinear susceptibilities and nonlinear optical response [6, 7], chemical and biological sensors [8, 9], optical energy transport [10-11], nonlinear thermal material [12-13], thermal therapy [14-15] and medicine [16]. Z-scan technique is one of the simplest and effective tools for measuring third order of nonlinear optics such as nonlinear refraction coefficient and absorption. It has been widely used in material characterization [17-18]. This method utilizes a focused laser beam that is intense enough to access nonlinearities in a sample. As the sample passes through the focal point of the beam, changes in its transmittance, due to nonlinear absorption and nonlinear refraction, can be measured by using an open aperture and close aperture experimental setup, respectively. In the open aperture technique the beam is focused into a detector, after passed through the sample. As the sample travels through the focus of the initial beam, the transmittance either increase or decrease (depending on the nonlinearity of the sample) and the detector receives more or less light than the linear transmittance, yielding a hump or dip in the curve of transmittance as a function of the sample position. For nonlinear refraction, after the beam passes through the sample, it is attenuated by a semi-closed aperture that usually allows less than 50% of the initial beam to be detected by the detector.

The converging and diverging of the beam (allowing more and less of the beam to pass through the aperture, respectively) due to the changes in the refractive index, a pre-focal valley and post-focal peak are observed for a positive change in refractive index. While a pre-focal peak and a post-focal valley is observed for a negative change in refraction index. In this paper we studied the effect of the concentration of Au/Pd ratio on their nonlinear refraction coefficient. Therefore, we report this effect using a single beam Z-scan technique. The results of this method are found to be in good agreement with the values of other works.

24.1 Methods Sample preparation

Colloidal dispersion of Au/Pd bimetallic nanoparticles was prepared by simultaneous reduction of gold and palladium ions in presence of poly (*N*-vinyl-2-pyrrolidone) (PVP) using ethanol as a reducing agent [19–22]. In a typical synthesis process, ethanol solutions of palladium chloride (0.033 mmol in 25 ml of ethanol) were prepared in advance by stirring dispersions of PdCl₂ powder in ethanol for 48 hrs. Solutions of tetrachloroauric acid (0.033 mmol in 25 ml of water) were prepared by dissolving the H₂AuCl₄ · 3H₂O crystals in water. For preparing bimetallic nanoparticles, solutions containing two metal ions were mixed in 50 ml of pure ethanol/water (1/1 v/v). 151 mg of PVP (Aldrich, average molecular weight 10,000) was added to the total metal ion content of 6.66 × 10⁻⁵ mol. The mixture solution was stirred and refluxed at about 100 °C for 1 hr. For the preparation of bimetallic nanoparticles with different Au/Pd ratios (10/1, 5/1, 2/1, 1/1, 1/2, 1/5 and 1/10), metal ion solutions of corresponding molar ratios were mixed and refluxed at 100 °C for 1 hr under agitation. The ethanol/water volumetric ratio of 1:1 and total ion content of 6.6 × 10⁻⁵ mol was maintained in the final 50 ml solution. The same procedure was followed to prepare the monometallic palladium (Pd) particles. For the preparation of monometallic gold (Au) particles, 23.5 ml of PVP solution (75.5 g in 23.5 ml of water) was added to the gold ion solution, and then an aqueous solution of NaBH₄ (0.066 mmol in 1.5 ml of water) was added to the resulting solution at 25 °C. The colloidal dispersions thus prepared are stable, with 3–5 nm in average diameter and narrow size distributions. In order to obtain the aqueous nanofluids containing Au/Pd bimetallic nanoparticles, the colloidal dispersions were subsequently dried in vacuum and the metallic particles were dissolved in water maintaining the same initial concentrations of metal content and were placed in a quartz cuvette of 1 mm thick for the optical and thermal optical measurements. All the experiments were performed at room temperature.

24.2 Z-scan technique

Among the techniques used to characterize the complex susceptibility, the most popular is the Z-scan method. Since its introduction in 1989 [23], this technique has gained importance due to its simplicity compared to other techniques used to measure the nonlinear refraction and absorption of optical materials. In addition to the simplicity of the experimental setup, a Z-scan measurement provides a sensitive method for the determination of the signal on values of the real and imaginary parts of χ .

The technique relies on the basic idea of relating the beam center intensity variation to the refractive index variation. This can be done by monitoring the normalized transmittance as a function of the sample path along the incident beam, for a positive nonlinearity. In the case of a negative nonlinearity, the curve is inverted.

The transmittance variation between peak and valley positions is proportional to the induced phase shift, $\Delta\Phi_0$ and therefore to the nonlinear refractive index (n_2) is calculated using the standard relations by means of the following equations [24-25]:

$$T(z, \Delta\Phi) = 1 + 4 \Delta\Phi_0 (z/z_0) / ((z/z_0)^2 + 1) (z/z_0)^2 + 9) \quad (24)$$

$$\Delta\Phi_0 = k n_2 I_0 L_{\text{eff}} \quad (24.1)$$


Where z is the position, z_0 is the Rayleigh length, $\Delta\Phi_0$ is the phase change due to the nonlinear refraction, n_2 is the nonlinear refractive index, $k = 2\pi/\lambda$ is the wave vector, $I_0 = 1.8 \times 10^3 \text{ W/cm}^2$ is the on-axis irradiance at focus (i.e., $z = 0$), and $L_{\text{eff}} = [1 - \exp(-\alpha_0 L)/\alpha_0]$ is the effective length of nonlinear medium, α_0 is the linear absorption coefficient of the samples (L denotes the sample thickness). The nonlinear refractive index, n_2 was calculated from ΔT_{p-v} being this parameter the value of peak to valley of data transmittance from the closed aperture Z – scan measurement which can be described as [24]:

$$\Delta T_{p-v} = 0.406 (1-S)^{0.25} |\Delta\Phi_0| \quad (24.2)$$

Here S is the linear transmittance of the aperture. Fig. 24 shows the schematic diagram of a single beam Z -scan experimental setup used in the present measurement. The experiments were performed using a CW Ar^+ laser beam, 514 nm wavelength (model Cyonics, Uniphase). The beam was focused to a small spot using a lens and the sample was scanned along a Z -axis by a motorized translation stage (Zaber). The transmitted light, in the far field, passed through the closed and open apertures and was recorded by the detectors D_c , D_o and D_r (reference detector).

The laser beam waist ω_0 at the focus length was measured to be 17 μm and the Rayleigh length was found to be satisfied the basic criteria of the Z -scan experiment.

Figure 24 Experimental setup for the nonlinear laser spectroscopy. The closed and open aperture signals are proportional to the real and imaginary parts of n_2 , respectively




A quartz optical cell, 1 mm thick, containing the specimen solution was translated across the focal region along the z -axial direction. All the measurements were carried out at room temperature for both closed aperture and open aperture configurations. Optical absorption spectra of the fluid samples were measured using a UV-Vis-NIR double beam spectrophotometer (Shimadzu UV3101PC). For transmission electron microscopic (TEM) observations, a drop of fluids was spread on a carbon coated copper microgrid. A JEOL JEM200 microscope was used for the low magnification of the samples.

24.3 Results and discussion


The absorption spectra of the Au/Pd nanofluids at different ratios (10/1, 5/1, 2/1, 1/1, 1/2, 1/5, 1/10) were measured by spectrophotometer. The measurements of absorption spectra were carried out at room temperature for visible wavelength, 350-800 nm. The spectra are shown in graphic 24.

Graphic 24 Optical absorption spectra of bimetallic nanoparticles with different Au/Pd



Graphic 24.1 displays a typical TEM images showing the particles with a uniform distribution and uniform shape. The average particle size obtained from TEM images was 3.9 nm.

Graphic 24.1 TEM image of Au/Pd particles with a average size of 3.9 nm




For closed aperture setup normalized transmittance is attributed to the nonlinearity of the refractive index which was considered here [26]. In the Figures 4-10 the closed aperture Z-scan curves obtained for Au/Pd nanofluid, at different concentration, at beam intensity of $I_0 = 1.8 \times 10^3 \text{ W/cm}^2$ are shown.

The circle symbols represent the experimental data while the solid lines are theoretical fits to the closed aperture. The theoretical transmittance curves presented in Figs. 4-10 are fitted very well with the experimental data and they show symmetry curves.

The peak follow by valley illustrate a self-focusing effect for a positive change in refraction. The solid line shows the theoretical fitting using a well-known normalized transmittance. The nonlinear refraction coefficients n_2 (cm^2/W) together with the values of linear absorption of all samples obtained in the present work are listed on Table 24. Graphic 24.8 shows the variation of the nonlinear refraction index coefficient as a function of concentrations for different ratios. The nonlinear refraction coefficient decrease with increasing of concentration (Au/Pd (10/1) to Au/Pd (1/1)). By other hand, if the concentration is inverse (Au/Pd (1/1) to Au/Pd (1/10)), the nonlinear refraction coefficient increases with the increasing of concentration. However the increase of nonlinear of refractive index coefficient with the concentration did not show a linear relationship as displayed in Fig. 11. In ref. [26], the authors studied the effect of concentration and particle size on nonlinearity of Au nano-fluid prepared by γ (^{60}Co) radiation.


From the experimental results of ref. [26], the authors obtained values of refractive index coefficient nonlinear of the same order found in this work.

Graphic 24.2 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration 10/1




The solid line is the best fitting of the standard closed aperture equations to the experimental data.


Graphic 24.3 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration 5/1



The solid line is the best fitting of the standard closed aperture equations to the experimental data.


Graphic 24.3 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration 2/1

The solid line is the best fitting of the standard closed aperture equations to the experimental data.

Graphic 24.4 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration 1/1


The solid line is the best fitting of the standard closed aperture equations to the experimental data.

Graphic 24.5 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration $\frac{1}{2}$




The solid line is the best fitting of the standard closed aperture equations to the experimental data.

Graphic 24.6 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration $\frac{1}{5}$



The solid line is the best fitting of the standard closed aperture equations to the experimental data.

24.7 Closed aperture Z-scan curve for Au/Pd nanoparticles at a concentration 1/10




The solid line is the best fitting of the standard closed aperture equations to the experimental data.

Table 24 Nonlinear optical properties of Au/Pd nanofluid at different concentrations. Molar ratios of 10/1, 5/1, 2/1, 1/1, 1/2, 1/5, 1/10 were measured at 514 nm laser beam

Au/Pd	ΔT_{pv}	$\Delta\phi_0$	$\alpha(\text{cm}^{-1})$	$n_2(\text{cm}^2/\text{W})$
10/1	1,48	3,99	13.5	$-13,0 \times 10^{-8}$
5/1	1,78	5,21	10	$-8,59 \times 10^{-8}$
2/1	1,03	3,02	7.9	$-3,93 \times 10^{-8}$
1/1	1,27	3,72	6.9	$-4,23 \times 10^{-8}$
1/2	1,45	4,25	8.9	$-6,23 \times 10^{-8}$
1/5	1,24	3,63	6.28	$-3,76 \times 10^{-8}$
1/10	1,84	5,39	6.84	$-6,08 \times 10^{-8}$

Graphic 24.8 Variation of the nonlinear refraction index coefficient as a function of Au/Pd ratio



24.4 Conclusions

The nonlinearity properties of Au/Pd nanofluid prepared at different concentrations have been successfully investigated using a single beam Z-scan method. A CW, Ar⁺ laser beam, at wavelength 514 nm, was used as excitation source. The Au/Pd nanofluid shows a good nonlinear response. The sign of the nonlinear refractive index is found to be positive and the magnitude is in the order of 10^{-8} - 10^{-7} cm²/W. A nonlinear relationship was obtained for nonlinear refractive index as a function of Au/Pd ratio. Until our knowledge these results are reported for the first time in the literature. These results showed that Au/Pd nano-fluid has significant values of nonlinear refractive index, thus it could be good candidate for nonlinear thermal material.

24.5 References

- Kumarakuru H, Cherns D, Montes de Oca M G, Fermin D J: TEM studies of stress relaxation in catalytic Au-Pd core-shell nanoparticles. *J of Phys: Conf Ser* 2012, 371: 012025.
- Hsu C, Huang C, Hao Y, Liu F: Au/Pd core-shell nanoparticles for enhanced electrocatalytic activity and durability. *Electrochemistry Communication* 2012, 23: 133-136.
- Montero M A, Gennero de Chialvo M R, Chialvo A C: Electrocatalytic activity of core-shell Au@Pt nanoparticles for the hydrogen oxidation reaction. *Int J of Hydrogen Energy* 2011, 36: 3811-3816.
- Liu F, Wechsler D, Zhang P: Alloy-structure-dependent electronic behavior and surface properties of Au-Pd nanoparticles. *Chem Phys Lett* 2008, 461: 254-259.
- Dirix Y, Bastiaansen C, Caseri W, Smith P: Oriented Pearl-Necklace Arrays of Metallic Nanoparticles in Polymers: A New Route Toward Polarization-Dependent Color Filters. *Adv Mater* 1999, 11: 223-227.
- Beecroft L L, Ober C K: Nanocomposite Materials for Optical Applications. *Chem Mater* 1997, 9: 1302-1317.
- Wang Y: Nonlinear optical properties of nanometer-sized semiconductor clusters. *Acc Chem Res* 1991, 24: 133-139.
- Elghanian R, Storhoff J J, Mucic R C, Letsinger R L, Mirkin C A: Selective colorimetric detection of polynucleotides based on the distance-dependent optical properties of gold nanoparticles. *Sciences* 1997, 277: 1078-1081.

Loo C, Lin A, Hirsch L, Lee M, Barton J, Halas N, West J, Drezek R: Nanoshell-Enabled Photonics-Based Imaging and Therapy of Cancer. *Tech Canc Res Treat* 2004, 3: 33-40.

Quinten M, Leitner A, Krenn J R, Aussenegg F R: Electromagnetic energy transport via linear chains of silver nanoparticles. *Opt Lett* 1998, 23: 1331-1333.

Brongersma M L, Hartman J W, Atwater H A: Electromagnetic energy transfer and switching in nanoparticle chain arrays below the diffraction limit. *Phys Rev B* 2000, 62: R16356- R16359.

Nadjari H, Abasi Azad Z: Determining the nonlinear coefficient of gold and silver nano-colloids using SPM and CW Z-scan. *Optics and Laser Technology* 2012, 44: 1629-1632.

Husinsky W, Ajami A, Nekvindova P, Svecova B, Pesicka J, Janecek M: Z-scan study of nonlinear absorption of gold nano-particles prepared by ion implantation in various types of silicate glasses. *Optics Communications* 2012, 285: 2729-2733.

Hirsch L R, Stafford R J, Bankson J A, Sershen S R, Price R E, Hazle J D, Halas N J, West J L: Nanoshell-mediated near-infrared thermal therapy of tumors under magnetic resonance guidance. *In Proceedings of the National Academy of Sciences (USA) PNAS* 2003, 100: 13549-13554.

Shahriari E, Mahmood Mat Yunus W, Saion E: Effect of particle size on nonlinear refractive index of Au nanoparticle in PVA solution. *Braz J of Phys* 2010, 40: 256-260.

Dhinaa A N, Palanisamy P K: Optical nonlinearity in measurement of urea and uric acid in blood. *Natural Science* 2010, 2: 106-111.

Guo S, Xu L, Wang H, You X, Ming N: Determination of optical nonlinearities in Cu(mpo)₂ by Z-scan technique. *Optical and Quantum Electronics* 2003, 35: 693-703.

18. Shahriari E, Mahmood Mat Yunus W, Naghavi K, Talib Z A.: Investigating of Nonlinear Refractive index Ag Nano-fluid Based on variation Particles Size. *J of Basic and Appl Sci* 2009, 1: 455-458.

Toshima N, Harada M, Yamazaki Y, Asakura K: Catalytic activity and structural analysis of polymer-protected gold-palladium bimetallic clusters prepared by the simultaneous reduction of hydrogen tetrachloroaurate and palladium dichloride. *J Phys Chem* 1992, 96: 9927-9933.

Wang Y, Toshima N: Preparation of Pd-Pt Bimetallic Colloids with Controllable Core/Shell Structures. *J Phys Chem B* 1997, 101: 5301-5306.

Asakura M K, Ueki Y, Toshima N: Catalytic activity and structural analysis of polymer-protected gold/palladium bimetallic clusters prepared by the successive reduction of hydrogen tetrachloroaurate (III) and palladium dichloride. *J Phys Chem* 1993, 97: 5103-5114.

Sánchez-Ramírez J F, Jiménez Pérez J L, Cruz Orea A, Gutiérrez Fuentes R, Bautista-Hernández A, Pal U: Thermal Diffusivity of Nanofluids Containing Au/Pd Bimetallic Nanoparticles of Different Compositions. *Journal of Nanoscience and Nanotechnology* 2006, 6: 1-6.

Sheik-Bahae M, Said A A, Van Stryland E W: High-sensitivity, single-beam n_2 measurements. *Opt Lett* 1989, 14: 955-957.

Sheik Bahae M, Said A A, Hwei Wei T, Hagan D J, Van Stryland E W: Sensitive measurement of optical nonlinearities using a single beam. *IEEE J of Quan Elect* 1990, 26:760-769.

Shabriari E, Mahmood Mat Yunus W: Single Beam Z-Scan Measurements of Nonlinear Refraction and Nonlinear Absorption Coefficients in Silver Nano-Fluid. *Am J of Eng and Appl Sci* 2010, 3(1): 98-101.

Shabriari E, Mahmood Mat Yunus W, Naghavi K, Talib Z A: Effect of concentration and particle size on nonlinearity of Au nano-fluid prepared by γ (^{60}Co) radiation. *Optics Communications* 2010, 283: 1928-1932.

